

Liming paste



1L

As with all wood finishing always do a test area first to safeguard against an undesirable outcome. This technical data sheet is merely a guide and not a guarantee. All products are formulated to the best of our knowledge. The information is given as a result of many years experience. This product has had extensive tests carried out.

Produced by Debal Coatings nv
Industrieweg 29 - 8800 Beveren-Roeselare
Belgium
tel. +32 (0) 51 30 11 40
fax +32 (0) 51 31 26 48
ciranova@ciranova.be

PRODUCT DESCRIPTION

Ready to use white paste to whitewash open pore wood.

TECHNICAL DATA

DENSITY	1,2
SOLID CONTENT	30%

USE

Especially for open grained wood such as oak, ash or elm.

PREPARATION

It is advisable to brush out the surface with a steel brush.

USER TIPS

Pre-treat the wood with FORTICO 1C, FORTICO 2C or HARDWAXOIL MAGIC or TITAN Ciranova[®]. Apply the liming paste generously with a brush. Let the liming paste dry for 4 hours. Then remove the surplus with sandpaper P180 until the desired result is reached.



DRYING TIMES

Can be sanded after +/- 4 hour.

AFTER TREATMENT

Dust free the surface. Protect the liming paste with the same product as used for the the base coat.

SPECIAL QUALITIES

This product is environmentally friendly. It is based on rye, wheat and recycled titan white. Based on water and linseed oil.